

## Product information

# Sasolwax 6213

printed on: 24.05.2016

Revision: 26.04.2016

<b>Property</b>	<b>Specification</b>	<b>Unit</b>	<b>Method</b>
Congealing point	45,0 .. 49,0	°C	ASTM D938
Needle penetration 25 °C	50 .. 80	1/10mm	ASTM D1321
Colour Saybolt	5 .. 30		ASTM D156
Reqs RAL/ Blend	Complies		RAL-GZ 041
Kin. viscosity 100 °C	3,5 .. 4,5	mm <sup>2</sup> /s	ASTM D7042

*This information is based on our present knowledge and experience. However, it implies no liability or other legal responsibility on our part, including any existing third party patent rights. In particular, no guarantee of properties in the legal sense is implied. We reserve the right to make any changes according to technological progress or further developments. The customer is not exempted from the obligation to conduct careful inspection and testing of incoming goods. Reference to trade names used by other companies is neither a recommendation, nor is it intended to suggest that similar products could not be used. All our business transactions shall be governed exclusively by our General Sales Conditions.*

### **Sasol Wax GmbH**

Gesellschaft mit beschränkter Haftung, Location Hamburg, Germany, Registration No. Hamburg HRB 73963

Managing Director: Edwin Vorsteveld

VAT-No. DE 118 922 039 parent company Sasol Wax Int. AG Tax No. 27/164/00088

[www.sasolwax.com](http://www.sasolwax.com) [wax@de.sasol.com](mailto:wax@de.sasol.com)